

## Technical Specifications

TEST PERFORMED	ASTM	RESULTS
Static coefficient of friction	C - 1028	Dry: 0.64 Wet: 0.61
Resistance to fire		Class 0
Freeze - thaw	C - 666	None (300 cycles)
Compressive strength	D - 170	8,000 - 12,000 psi
Modulus of rupture	C - 99	1,250 psi
Flexural strength	C - 880	1,572 psi
Water absorption	C - 97	5.2%